

IS 1328 : 1996  
(Reaffirmed 2007)

(Reaffirmed 2011)

(Reaffirmed 2017)

(Reaffirmed 2022)

भारतीय मानक  
परतदार सजावटी प्लाईवुड - विशिष्ट  
( तीसरा पुनरीक्षण )  
*Indian Standard*

VENEERED DECORATIVE PLYWOOD-  
SPECIFICATION

*(Third Revision)*

---

First Reprint DECEMBER 2000

ICS 79.060.10

© BIS 1996

BUREAU OF INDIAN STANDARDS  
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG  
NEW DELHI 110002

## *Indian Standard*

**AMENDMENT NO. 1 JUNE 2000  
TO  
IS 1328 : 1996 VENEERED DECORATIVE  
PLYWOOD — SPECIFICATION**

*( Third Revision )*

*( Second cover page, Foreword )* — Insert the following after fourth para as a separate para:

'A scheme of labelling environment friendly products to be known as ECO Mark has been introduced at the instance of the Ministry of Environment and Forests (MEF), Government of India. The ECO Mark shall be administered by the Bureau of Indian Standards (BIS) under the *BIS Act*, 1986 as per the Resolution No. 71 dated 21 February 1991 and Resolution No. 425 dated 28 October 1992 published in the Gazette of the Government of India. For a product to be eligible for ECO Mark, it shall also carry the Standard Mark of the BIS besides meeting additional environment friendly requirements. For this purpose, the Standard Mark of BIS would be a single mark being a combination of the ISI Mark and the Eco logo. Requirements to be satisfied for a product to qualify for the BIS Standard Mark for Eco friendliness, will be included in the relevant published Indian Standards through an amendment. These requirements will be optional; manufacturing units will be free to opt for ISI Mark alone also.

The amendment pertaining to Eco criteria is based on the Gazette Notification No. 170 dated 18 May 1996 for Wood Substitutes as Environment Friendly Products published in the Gazette of Government of India'.

*( Page 1, clause 5.1.1 )* — Insert the following at the end of the clause:

'For ECO Mark only species of wood from sources other than natural forests such as wood from rubber, coconut, cashew, industrial and social forestry plantations, etc and shade trees from tea and coffee estates shall be used.'

*( Page 1, clause 5.1.2 )* — Insert the following at the end of the clause:

'For ECO Mark, only species of wood from sources other than natural forests such as wood from rubber, coconut, cashew, industrial and social forestry plantations, etc and shade trees from tea and coffee estates shall be used.'

**Amend No. 1 to IS 1328 : 1996**

( Page 1, clause 5.3 ) — Insert the following at the end of the clause:

'For ECO Mark, the plywood shall conform to the requirements specified for MR type in IS 303 : 1989 for ECO Mark purposes.'

( Page 2, clause 12.2 ) — Insert the following at the end of the clause:

'For ECO Mark, the material used for packaging of the plywood shall be recyclable, reusable or biodegradable.'

( Page 2, clause 12.2 ) — Insert the following new clauses after 12.2 and renumber the subsequent clauses:

**'13 OPTIONAL REQUIREMENTS FOR ECO MARK**

**13.1 General Requirements**

**13.1.1** The veneered decorative plywood shall conform to the requirements of quality and performance as specified in this standard.

**13.1.2** The manufacturer shall produce to BIS environmental consent clearance from the concerned State Pollution Control Board as per the provisions of the *Water (Prevention and Control of Pollution) Act, 1974* and *Air (Prevention and Control of Pollution) Act, 1981* and *Water (Prevention and Control of Pollution) Cess Act, 1977* alongwith the authorization, if required under the *Environment (Protection) Act, 1986* while applying for ECO Mark appropriate with enforced rules and regulations of Forest Department.

**13.2 Specific Requirements**

The veneered decorative plywood shall conform to the specific requirements given for ECO Mark under relevant clauses of the standard.

NOTE — The manufacturer shall provide documentary evidence by way of certificate or declaration to the Bureau of Indian Standards while applying for ECO Mark.'

( Page 2, renumbered clause 14.1 ) — Insert the following matter at the end of clause:

'e) The criteria for which the plywood has been labelled as ECO Mark.'

( CED 20 )

**AMENDMENT NO. 2 AUGUST 2002  
TO  
IS 1328 : 1996 VENEERED DECORATIVE  
PLYWOOD — SPECIFICATION  
( Third Revision )**

( Page 1, clause 4 ) — Substitute the following for the existing clause:

**‘4 GRADES AND TYPES**

**4.1** Decorative plywood shall be of two grades, namely, BWR and MR.

**4.2** Decorative plywood shall be of two types, namely, Type 1 and Type 2, the two types conforming to the requirements given in 7.’

( Page 1, clause 5.2 ) — Substitute the following for the existing clause:

**‘5.2 Adhesive**

The adhesive for bonding veneers shall be MR and BWR type synthetic resin adhesive, conforming to IS 848:1974, for MR and BWR grade veneered decorative plywood respectively.’

[ Page 1, clause 5.3 ( see also Amendment No. 1 ) ] — Substitute the following for the existing clause:

**‘5.3 Plywood**

Plywood, when used in the manufacture of veneered decorative plywood of MR and BWR grade, shall be MR and BWR type conforming to IS 303:1989.’

( Page 2, clause 8.1 ) — Insert the following note at the end of the clause:

‘NOTE — Any other dimension as agreed to between the manufacturer and the purchaser may be used.’

( Page 2, clause 11.1.2 ) — Substitute the following for the existing clause:

**‘11.1.2 Water Resistance Test**

Veneered decorative plywood of MR and BWR grade, when tested in the manner specified in 11.1.2.1 and 11.1.2.2 respectively, shall not show delamination or blister formation.’

**Amend No. 2 to IS 1328 : 1996**

( *Page 2, clause 11.1.2.1* ) — Insert the following new clause after 11.1.2.1:

**'11.1.2.2 Three test specimens of size 250 mm × 100 mm shall be prepared from each of the boards selected and boiled in water for 8 hours and dried for 16 hours at a temperature of  $65 \pm 2^{\circ}\text{C}$  and then followed by two more cycles of soaking and drying under the same conditions described above.'**

[ *Page 2, clause 13.1(d)* ] — Substitute 'Grade and Type' for 'Type(see 7)'.

( CED 20 )

**AMENDMENT NO. 3 JANUARY 2005  
TO  
IS 1328 : 1996 VENEERED DECORATIVE  
PLYWOOD — SPECIFICATION  
( Third Revision )**

( Page 2, clause 8 ) — Substitute the following for the existing:

**8 DIMENSIONS AND TOLERANCES**

**8.1** The dimensions of plywood boards shall be as follows:

2 400 mm × 1 200 mm	2 100 mm × 900 mm
2 100 mm × 1 200 mm	1 800 mm × 900 mm
1 800 mm × 1 200 mm	

**8.2 Thickness**

The thickness of plywood board shall be 3 mm, 4 mm, 6 mm, 9 mm, 12 mm, 19 mm and 25 mm.

NOTE — Any other dimensions (length, width and thickness) as agreed to between the manufacturer and the purchaser may also be used.

**8.3 Tolerances**

Tolerances on the nominal sizes of finished boards shall be as follows:

<i>Dimension</i>	<i>Tolerance</i>
Length	+6 -0 mm
Width	+3 -0 mm
Thickness:	
i) Less than 6 mm	±10 percent
ii) 6 mm and above	±5 percent
Edge straightness	2 mm per 1000 mm or 0.2 percent
Squareness	2 mm per 1000 mm or 0.2 percent

NOTE — Edge straightness and squareness shall be tested as per Annex C.

**Amend No. 3 to IS 1328 : 1996**

( Page 2, clause 9 ) — Substitute the following for the existing:

**9 FINISH**

**9.1** The decorative plywood shall be uniform in thickness within the tolerance specified in 8.3.

**9.2** The edges of the decorative plywood shall be sanded to a smooth finish, trimmed straight and square. Edge straightness and squareness when tested as per Annex C shall be within the tolerances specified in 8.3.

( Page 3, Annex B ) — Insert the following Annex C after Annex B:

**ANNEX C**  
( Clause 9.2 )

**METHOD OF TEST FOR EDGE STRAIGHTNESS AND SQUARENESS**

**C-1 PROCEDURE FOR EDGE STRAIGHTNESS**

**C-1.1** The straightness of the edges and ends of plywood shall be verified against a straight edge not less than the full length of the plywood. If the edge on the end of the plywood is convex, it shall be held against the straight edge in such a way as to give approximately equal gap at each end. The largest gap between the straight edge and the edge shall be measured to the nearest millimetre and recorded.

**C-2 PROCEDURE FOR SQUARENESS**

**C-2.1** The squareness of plywood shall be checked with a 1 200 mm × 1 200 mm square, by applying one arm of the square to the plywood. The maximum width of the gap shall be recorded.

( Page 4, Annex C ) — Rename 'ANNEX C' as 'ANNEX D'.

( Second cover page, Foreword, fifth para ) — Substitute 'Annex D' for 'Annex C'.

( CED 20 )

Reprography Unit, BIS, New Delhi, India

**AMENDMENT NO. 4 JUNE 2005  
TO  
IS 1328 : 1996 VENEERED DECORATIVE  
PLYWOOD — SPECIFICATION**

*( Third Revision )*

*( Page 1, clause 6.1, first sentence )* — Substitute the following for existing:

'Decorative veneers shall be rotary cut or sliced and shall have a thickness of not less than 0.3 mm and not more than 1.0 mm.'

CED 20 )

Reprography Unit, BIS, New Delhi, India



**AMENDEMNT NO. 5 SEPTEMBER 2006  
TO  
IS 1328 : 1996 VENEERED DECORATIVE  
PLYWOOD — SPECIFICATION**

*( Third Revision )*

[Page 2, clause 13, Title (see also Amendment No. 1)] – Substitute  
'ADDITIONAL' for 'OPTIONAL'.

( CED 20 )

---

Reprography Unit, BIS, New Delhi, India

**AMENDMENT NO. 6 AUGUST 2007  
TO  
IS 1328 : 1986 VENEERED DECORATIVE  
PLYWOOD — SPECIFICATION**

*( Third Revision )*

*{Page 2, clauses 11.1.2.1 and 11.1.2.2 (see also Amendment No. 2)}* —  
Insert the following Note at the end of the above clauses:

*NOTE: - The cycles of drying or soaking can be made up of a number of shorter periods of drying or soaking. In such instances, the specimen shall be kept in air at  $27 \pm 2^{\circ}\text{C}$  in between the shorter periods constituting the drying cycle and be kept submerged in water at  $27 \pm 2^{\circ}\text{C}$  in between the shorter periods constituting the soaking cycle.*

(CED 20)

---

Reprography Unit, BIS, New Delhi, India

## Wood Products Sectional Committee, CED 20

### FOREWORD

**This Indian Standard (Third Revision) was adopted by the Bureau of Indian Standards, after the draft finalized by the Wood Products Sectional Committee had been approved by the Civil Engineering Division Council.**

**Decorative plywood is used in panelling work in buildings, interior lining of railway coaches, buses and ships and for furniture and general interior decoration. In view of the wide field of its application, decorative plywood has to be durable, of sound construction and highest quality.**

**This standard was first published in 1958 and was subsequently revised in 1970 and 1982 wherein modifications in the list of species and provision of Types 1 and 2 of plywood were made. This third revision of the standard is being brought out to incorporate modifications found necessary in the present day context. This revision permits use of any species of timber for cores and backs of veneered decorative plywood. The grade of plywood has been limited to only Moisture Resistant (MR) and recommended definite thicknesses have been included. Also the references to referred Indian Standards have been updated.**

**In the formulation of this standard due weightage has been given to international co-ordination among the standards and practices prevailing in different countries in addition to relating it to the practices in the field in this country.**

**The Committee responsible for the preparation of the standard is given at Annex C.**

**For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2 : 1960 'Rules for rounding off numerical values (*revised*)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.**

*Indian Standard*  
**VENEERED DECORATIVE PLYWOOD —  
SPECIFICATION**  
*( Third Revision )*

**1 SCOPE**

This standard covers types of plywood with ornamental veneers on one or both faces used for decorative purposes, such as furniture making, panelling of all kinds, including panelling for railway coaches, buses and ships.

**2 REFERENCES**

The Indian Standards listed in Annex A are necessary adjuncts to this standard.

**3 TERMINOLOGY**

**3.1** For the purpose of this standard, the following definition in addition to those given in IS 707 : 1976 shall apply.

**3.1.1 Insect Hole**

Open hole caused by wood boring insects.

**4 TYPES**

Decorative plywood shall be of two types, namely Type 1 and Type 2, the two types conforming to the requirements given in 7.

**5 MATERIALS**

**5.1 Timber**

**5.1.1** The species of timber for the decorative face veneer in decorative plywood shall be specified by the purchaser while placing the order. The species of timber commonly used for decorative veneers or decorative plywood are given in Annex B.

**5.1.2** Any species of timber may be used for cores and backs of decorative veneered plywood. However, a list of species, given in Annex B of IS 303 : 1989 may be used for guidance. Non-durable timbers and sapwood of all other timbers shall be given a preservative treatment. The preservative used shall be such as not to impart any colour or lasting smell, oiliness or stain to the plywood and shall not adversely affect the glueing of the veneer and the waxing and polishing of the surface.

**5.2 Adhesive**

The adhesive for bonding of veneers shall be MR type synthetic resin adhesive, conforming to IS 848 : 1974.

**5.3 Plywood**

Plywood, when used in the manufacture of veneered decorative plywood, shall be of MR type conforming to IS 303 : 1989.

**6 MANUFACTURE**

**6.1 Decorative Veneers**

Decorative veneers shall be rotary cut or sliced and shall be not more than 1.0 mm in thickness. The veneers shall be spliced or taped at the edges. The veneers may have end grain joints in cases of special matching like centre-matching, V-matching, etc.

**6.2** Veneers forming any one ply and the corresponding ply on the opposite side of the central plane of plywood shall be of the same species of timber and of the same nominal thickness, except in case of faces where they shall be of such thickness and strength as to balance each other.

**7 REQUIREMENTS**

**7.1 Type 1**

Type 1 veneered decorative plywood shall comply with the requirements specified in 7.1.1 to 7.1.4.

**7.1.1** Open splits, checks or open joints not more than 150 mm in length and 0.5 mm in width shall be permissible provided the same are rectified with a veneer insert bonded with synthetic resin adhesive, as the case may be, and further provided that the insert matches with the surrounding veneer in colour as well as in figure.

**7.1.2** The decorative veneered surface shall be free from torn grain, dead knots, wote, discolouration and sapwood.

**7.1.3** The decorative veneered surface shall be selected for figure, texture, colour and grain characteristics. It shall be free from all manufacturing and wood defects except to the extent permitted under 7.1.1. All veneers shall be matched or mismatched to achieve a decorative effect in colour, figure and grain.

**7.1.4** If the purchaser requires boards with the decorative veneers matched to a particular design,

## IS 1328 : 1996

for example, quartered, centred, diamond or V-matched or where it is required that there should be complete absence of pin knots, it shall be so specified. If certain number of decorative matched plywood panels are required to form a group to give an overall general effect it shall be so specified by the purchaser giving the number of panels in each such group.

### 7.2 Type 2

Type 2 veneered decorative plywood shall comply with the requirements specified in 7.2.1 to 7.2.3.

7.2.1 Open splits, checks, or open joints not more than 200 mm in length and 1 mm in width shall be permissible, provided these are rectified in the manner specified under 7.1.1. Tight knots and patches not more than 25 mm in diameter, and pin knots not more than 4 mm in diameter, shall be permissible.

7.2.2 The decorative veneer shall be free from the torn grain, dead knots, dots and discolouration. Sapwood, if it does not affect the appearance, shall be permissible.

7.2.3 The decorative veneered surface shall be selected for figure, texture, colour and grain characteristics. It shall be free from all manufacturing and wood defects, except to the extent permitted in 7.2.1 and 7.2.2. All veneers shall be matched or mis-matched to achieve a decorative effect in colour, figure and grain.

## 8 DESIGNATION OF DIMENSIONS AND TOLERANCES

8.1 The dimensions and tolerances (including on thickness) of plywood shall be as given in IS 12049 : 1987.

### 8.2 Thickness

Unless otherwise specified, thickness of the plywood boards shall be 3 mm, 4 mm, 6 mm, 9 mm, 12 mm, 19 mm or 25 mm.

## 9 FINISH

9.1 The decorative plywood shall be uniform in thickness within the tolerance limits specified in 8.1.

9.2 The edges of the decorative plywood shall be trimmed square within 3 mm and sanded to a smooth finish.

## 10 SAMPLING AND CRITERIA FOR CONFORMITY

The method of drawing representative samples and criteria for conformity shall be as per IS 7638 : 1986.

## 11 TESTS

11.1 Test boards selected as described in 10 shall be subjected to the test specified in 11.1.1 and 11.1.2.

### 11.1.1 Moisture Content

Decorative veneered plywood of either type when tested in accordance with IS 1734 (Part 1) : 1983 shall have a moisture content of not less than 5 percent and not more than 15 percent.

### 11.1.2 Water Resistance Test

Decorative veneered plywood of either type, when tested in the manner specified in 11.1.2.1, shall not show delamination or blister formation.

11.1.2.1 Three test specimens of size 250 mm × 100 mm shall be prepared from each of the boards selected and submerged in water at 60±2°C for a period of 3 hours and dried for 8 hours at a temperature of 65±2°C and then followed by two more cycles of soaking and drying under the same conditions described above.

## 12 INSPECTION AND DELIVERY

### 12.1 Inspection

All boards shall be visually inspected to ensure that the decorative veneered sides conform to the requirements specified in 7. They shall also be inspected for delamination, blisters or surface defects.

### 12.2 Delivery

The decorative plywood shall be supplied in a clean and dry condition and shall be suitably packed according to approved trade practice, unless otherwise specified by the purchaser.

## 13 MARKING

13.1 Each plywood board shall be legibly and indelibly marked or stamped with the following on the face of board near one corner:

- a) Indication of the source of manufacture.
- b) Year of manufacture,
- c) Batch No., and
- d) Type (*see* 7).

### 13.2 BIS Certification Marking

The decorative veneered plywood may also be marked with the Standard Mark.

13.2.1 The use of the Standard Mark is governed by the *Bureau of Indian Standards Act, 1986* and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

## ANNEX A

### (Clause 2)

#### LIST OF REFERRED INDIAN STANDARDS

<i>IS No.</i>	<i>Title</i>	<i>IS No.</i>	<i>Title</i>
303 : 1989	Specification for plywood for general purposes ( <i>third revision</i> )	1734 (Part 1) : 1983	Methods of test for plywood: Part 1 Determination of density and moisture content ( <i>second revision</i> )
707 : 1976	Glossary of terms applicable to timber technology and utilization ( <i>second revision</i> )	7638 : 1986	Methods of sampling for plywood, fibre hardboard, insulation boards and particle boards ( <i>first revision</i> )
848 : 1974	Specification for synthetic resin adhesive for plywood (phenolic and aminoplastic) ( <i>first revision</i> )	12049 : 1987	Dimensions and tolerances relating to wood based panel materials

## ANNEX B

### (Clause 5.1.1)

#### SPECIES OF TIMBER COMMONLY USED FOR DECORATIVE VENEERS OR DECORATIVE PLYWOOD

<i>Standard Trade Name</i>	<i>Botanical Name</i>	<i>Abbreviation</i>
Champ	<i>Michelia</i> spp.	CHM
Chaplash	<i>Artocarpus chapalsha</i>	CHP
Chickrassy	<i>Chukrasia tabularis</i>	CHI
Dipika (Lapse)	<i>Mansonia dipikae</i>	DIP
Kanju	<i>Holoptelea integrifolia</i>	KAN
Kokko	<i>Albizia lebbek</i>	KOK
Laurel	<i>Terminalia tomentosa</i>	LAU
Mahogany	<i>Swietenia</i> spp.	MAG
Malai	<i>Shorea assamica</i>	MAK
Maple	<i>Acer</i> spp.	MAP
Padauk	<i>Pterocarpus dalbergioides</i>	PAA
Poon	<i>Calophyllum</i> spp.	POO
Rosewood	<i>Dalbergia latifolia</i>	ROS
Silver grey	<i>Terminalia bialata</i> (Heartwood)	SGR
Silver oak	<i>Grevillea robusta</i>	SOA
Siris	<i>Albizia chinensis</i> (syn. <i>A. stipulata</i> )	SIR
Sissoo	<i>Dalbergia sisso</i>	SIS
Teak	<i>Tectona grandis</i>	TEA
Walnut	<i>Juglans</i> spp.	WAL
White cedar	<i>Dysoxylum malabaricum</i>	WCE

IS 1328 : 1996

**ANNEX C**  
**( Foreword )**  
**COMMITTEE COMPOSITION**

Wood Products Sectional Committee, CED 20

<i>Chairman</i>	<i>Representing</i>
DR P. M. GANAPATHY	Indian Plywood Industries Research and Training Institute, Bangalore
<i>Members</i>	
SHRI B. S. ASWATHANARAYANA	Indian Plywood Industries Research and Training Institute, Bangalore
SHRI P. D. AGARWAL	Public Works Department, Uttar Pradesh
SHRI V. S. SINGH ( <i>Alternate</i> )	
SHRI K. K. BARUAH	Forest Department, Government of Assam, Guwahati
SHRI T. K. DAS ( <i>Alternate</i> )	
MAJ S. S. BISHT	Directorate of Standardization, Ministry of Defence, New Delhi
SHRI B. S. NARULA ( <i>Alternate</i> )	
SHRI N. M. CHACHAN	Plywood Manufacturers' Association of West Bengal, Calcutta
SHRI B. B. ROY ( <i>Alternate</i> )	
SHRI A. K. CHATTERJEE	Directorate General of Technical Development, New Delhi
SHRI O. P. SHARMA ( <i>Alternate</i> )	
SHRI P. G. DESHMUKH	Indian Institute of Packaging, Bombay
SHRI P. L. NAGARSEKHAR ( <i>Alternate</i> )	
SHRI HARISH KHATTAN	Andaman Chamber of Commerce and Industry, Port Blair
SHRI J. L. BOTHRA ( <i>Alternate</i> )	
SHRI A. K. KADERKUTTY	The Western Indian Plywood Ltd, Baliapatam
SUPERINTENDING ENGINEER (S&S)	Central Public Works Department, New Delhi
EXECUTIVE ENGINEER (SRS) ( <i>Alternate</i> )	
SHRI RAVINDER KUMAR	Ministry of Defence (R&D), New Delhi
SHRI D. K. KANUNGO	National Test House, Calcutta
DR YOGESH CHANDRA NIHAVAN ( <i>Alternate</i> )	
SHRI K. S. LAULY	The Indian Plywood Manufacturing Company Ltd, Bombay
SHRI P. T. S. MENON ( <i>Alternate</i> )	
SHRIMATI P. MEENAKSHI	Engineer-in-Chief's Branch, Army Headquarters, New Delhi
I.T-COL PRADEEP KUMAR ( <i>Alternate</i> )	
DR A. N. NAYAR	In personal capacity (C-29 Inderpuri, New Delhi 110012)
PRESIDENT	Federation of Indian Plywood and Panel Industry, New Delhi
EXECUTIVE DIRECTOR ( <i>Alternate</i> )	
SHRI S. K. SANGANERIA	Assam Plywood Manufacturers' Association, Tinsukhia
SHRI K. SANKARAKRISHNAN	South Indian Plywood Manufacturers' Association, Trivandrum
SHRI S. N. SANYAL	Forest Products Division, FRI, Dehra Dun
SHRI N. K. SHUKLA ( <i>Alternate</i> )	
SHRI S. N. SANYAL	Indian Academy of Wood Science, Bangalore
SHRI K. S. SHUKLA ( <i>Alternate</i> )	
SHRI H. V. SARDA	Mangalam Timber Products Ltd, Calcutta
SHRI AMAR KUMAR ( <i>Alternate</i> )	
SHRI F. C. SHARMA	Directorate General of Civil Aviation, New Delhi
SHRI N. M. WALECHA ( <i>Alternate</i> )	
DR Y. SINGH	Central Building Research Institute (CSIR), Roorkee
SHRI L. K. AGGARWAL ( <i>Alternate</i> )	
SHRI J. K. SINHA	Ministry of Defence (DGQA), Kanpur
SHRI RAMA CHANDRA ( <i>Alternate</i> )	
DR N. SRIRAM	NUCHEM Ltd, Faridabad
SHRI N. K. UPADHAYAY	Directorate General of Supplies and Disposals, New Delhi
SHRI M. ZAFRULLA	Sitapur Plywood Manufacturers Ltd, Sitapur
SHRI TRIDIB SEN ( <i>Alternate</i> )	
SHRI VINOD KUMAR,	Director General, BIS ( <i>Ex-officio Member</i> )
Director (SG) and Head (Civ Engg)	

*Secretary*  
SHRIMATI RACHNA SEHGAL  
Assistant Director (Civ Engg), BIS

( Continued on page 5 )

( Continued from page 4 )

Plywood and Veneers Subcommittee, CED 20 : 1

<i>Convener</i>	<i>Representing</i>
SHRI V. SIVANANDA	Indian Plywood Industries Research and Training Institute, Bangalore
<i>Members</i>	
SHRI A. K. ANANTHANARAYANA	Institute of Wood Science and Technology, Bangalore
SHRIMATI B. S. KAMALA ( <i>Alternate</i> )	
SHRI P. D. AGARWAL	Public Works Department, Uttar Pradesh
SHRI V. S. SINGH ( <i>Alternate</i> )	
SHRI J. L. BOTHRA	Andaman Chamber of Commerce and Industry, Port Blair
SHRI S. C. MALHOTRA ( <i>Alternate</i> )	
SHRI N. M. CHACHAN	Plywood Manufacturers' Association of West Bengal, Calcutta
SHRI B. B. ROY ( <i>Alternate</i> )	
SHRI P. R. CHANDERSEKHAR	Directorate General of Civil Aviation, New Delhi
SHRI A. K. CHATTERJEE	Directorate General of Technical Development, New Delhi
SHRI O. P. SHARMA ( <i>Alternate</i> )	
SHRI SUDEEP CHITLANGIA	Sarda Plywood Industries Ltd, Calcutta
SHRI K. K. MAHESHWARI ( <i>Alternate</i> )	
SHRI P. G. DESHMUKH	Indian Institute of Packaging, Bombay
SHRI S. C. PURUSHOTHAMAN ( <i>Alternate</i> )	
DIRECTOR	Indian Plywood Industries Research and Training Institute, Bangalore
DR R. GNANAHARAN	Kerala Forest Research Institute, Peechi
SHRI V. K. GUPTA	Forest Research Institute, Forest Products Division, (Timber Mechanics), Dehra Dun
SHRI T. K. JACOB	Veneers and Laminations (India) Ltd, Cochin
SHRI A. K. KADERKUTTY	The Western India Plywood Ltd, Cannanore
SHRI HARISH KHAITAN	Andamans Timber Industries Ltd, Calcutta
SHRI YASH PODDAR ( <i>Alternate</i> )	
SHRI B. C. KHARBANDA	Kerala State Wood Industries Ltd, Nilampur
SHRI M. SURESH BABU ( <i>Alternate</i> )	
SHRI K. S. LAULY	The Indian Plywood Manufacturing Co Ltd, Bombay
SHRI P. T. S. MENON ( <i>Alternate</i> )	
SHRI S. P. MITTAL	Kitply Industries Ltd, Tinsukhia
SHRI R. S. BASSI ( <i>Alternate</i> )	
MAJ S. S. BISHT	Directorate of Standardization, New Delhi
SHRI B. S. NARULA ( <i>Alternate</i> )	
PRESIDENT	Assam Plywood Manufacturers' Association, Tinsukhia
SHRI K. S. SHUKLA	Forest Research Institute, Forest Products Division (Composite Wood), Dehra Dun
DR S. P. SINGH ( <i>Alternate</i> )	
SUPERINTENDING ENGINEER (S&S)	Central Public Works Department, New Delhi
EXECUTIVE ENGINEER (S&S) ( <i>Alternate</i> )	
SHRI N. K. UPADHYAY	Directorate General of Supplies and Disposals, New Delhi
SHRI MOIZ VAGH	South Indian Plywood Manufacturers' Association, Kottayam
SHRI A. R. VJAYENDRA RAO	Central Food Technological Research Institute (CSIR), Mysore
SHRI N. BALASUBRAMANYAN ( <i>Alternate</i> )	
SHRI M. ZAFRULLA	Sitapur Plywood Manufacturers Ltd, Sitapur
SHRI TRIDIB SEN ( <i>Alternate</i> )	



## Bureau of Indian Standards

BIS is a statutory institution established under the *Bureau of Indian Standards Act, 1986* to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

### Copyright

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publication), BIS

### Review of Indian Standards

Amendments are issued to standards as the need arises on the basis of comments. Standards are also reviewed periodically; a standard along with amendments is reaffirmed when such review indicates that no changes are needed; if the review indicates that changes are needed, it is taken up for revision. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition by referring to the latest issue of 'BIS Handbook' and 'Standards: Monthly Additions'.

This Indian Standard has been developed from Doc: No. CED 20 ( 5508 ).

### Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected

### BUREAU OF INDIAN STANDARDS

#### Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002  
Telephones: 323 01 31, 323 3375, 323 94 02

Telegrams: Manaksanstha  
(Common to all offices)

#### Regional Offices:

Central : Manak Bhavan, 9 Bahadur Shah Zafar Marg  
NEW DELHI 110002

Telephone  
323 76 17, 323 38 4:

Eastern : 1/14 C.I.T. Scheme VII M, V.I.P. Road, Kankurgachi  
CALCUTTA 700054

{ 337 84 99, 337 85 61  
{ 337 86 26, 337 91 20

Northern : SCO 335-336, Sector 34-A, CHANDIGARH 160022

{ 60 38 43  
{ 60 20 25

Southern : C.I.T. Campus, IV Cross Road, CHENNAI 600113

{ 235 02 16, 235 04 42  
{ 235 15 19, 235 23 15

Western : Manakalaya, E9 MIDC, Marol, Andheri (East)  
MUMBAI 400093

{ 832 92 95, 832 78 58  
{ 832 78 91, 832 78 92

Branches : AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR.  
COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI.  
HYDERABAD. JAIPUR. KANPUR. LUCKNOW. NAGPUR.  
PATNA. PUNE. RAJKOT. THIRUVANANTHAPURAM.